

C	ИI	ш
Э	N	U

Grass Zone Yarn/Color

Grass Zone Denier

Thatch Zone Yarn/Color

Thatch Zone Denier

Grass Zone Yarn Shape

Finished Pile Height

Finished Pile / Total Weight

Backing

Tuft Gauge

Tuft Bind

Permeability

Features

Test Data

GTR60

PE / Sport Green / Olive

7,200/8

PE/PP Blend / Green / Tan

5,000/8

Diamond Mono

2"

60 oz. / 89 oz.

13PP/18PET 2pt / 22oz. EnviroLoc+™

3/8"

> 8 lbs.

> 300 inches p/hr

Sanitized*, EnviroLoc+™, StatBlock™ Anti-Static, DualChill™ IR Reflective, Deluster, UV Stabilizers

SYNNATURAL 60 GTR

SYNNatural 60 GTR represents the pinnacle of turf innovation. Its multi-directional technology blends straight and semi-texturized fibers for a realistic, natural appearance, enhanced by reduced sheen. Crafted with 70% renewable content, it is made of both plant-based and PCR materials. This turf delivers unparalleled authenticity, setting a new standard in landscape design.



SUPER YARN™ TECHNOLOGY

SANITIZED® ANTIMICROBIAL **DUALCHILL™**IR RFFI FCTIVF

STATBLOCK™ ANTI-STATIC



LIMITED LIFETIME WARRANTY



ENVIROLOC+ ™ BACKING SYSTEM



ULTRA-REALISTIC COLOR BLEND



PATENTED MULTI-DIRECTIONAL DESIGN





















SYNNATURAL 60 GTR



Official Synthetic Surface

Primary Yarn Polymer	Polyethylene		
Primary Yarn Cross Section	Diamond Mono		
Primary Yarn Color	Sport Green / Olive		
Fabric Construction	Tufted		
Semi-Texturized Yarn Polymer	Polyethylene		
Semi-Texturized Yarn Polymer Semi-Texturized Yarn Color	Polyethylene Field Green / Lime		

Primary Backing	13PP/18PET 2pt	
Coating Type	22 oz. EnviroLoc+	
Primary Yarn Denier / Ends	7,200/8	
Semi-Texturized Denier / Ends	7,200 / 8	
Thatch Yarn Denier / Ends	5,000 / 8	
Warranty Period	Limited Lifetime	

FINISH FABRIC	ENGLISH	SYSTEM	ASTM TEST
Nominal Specification	Value	Units	Method
Pile Height (Nominal)	2	inches	D-5823
Face Weight	60	oz/yd²	D-5848
Total Fabric Weight	89	oz/yd²	D-5848
Primary Backing Weight	6	oz/yd²	D-5848
Secondary Coating Weight	22	oz/yd²	D-5848
Tuft Bind	> 8	lbs.	D-1335
Grab Tear Strength (Average)	> 200	lbs.	D-5034
Total Yarn Linear Density	19,400	Denier	D-1577
Elongation to Break	> 30	%	D-2256
Yarn Breaking Strength	> 20	lbs.	D-5793
Machine Gauge	3/8	inches	D-5793
Flammability	-	-	-
Water Permeability	> 300	in/hr	D-1551
Fabric Width	15	ft	-